

Fast-setting, self-leveling, polymer modified cementitious screed

Description

Fast-setting, self-leveling cementitious mortar for leveling floor substrates, enriched with polymer components (resins). It features high mechanical strength, superb adhesion to the substrate, excellent workability, fast-hardening and slightest shrinkage. It provides a smooth, flat and durable final surface, ready to be covered in a very short time with any further finishing layer. Suitable for layers 1-10 mm thick.

It is classified as a screed material CT-C30-F7-AR4 (grey) and CT-C30-F7-AR6 (white) according to EN 13813.

Fields of application

Ideal for fast smoothing and leveling of concrete floors, cement screeds, mosaic floors etc. that are going to be covered with all kinds of tiles, carpet, parquet, vinyl tiles etc. It is suitable only for interior use. It may be left as a final topping layer in basements, attics, home storerooms etc. Suitable for leveling floors with underfloor heating systems. FLOWCRET 1-10 EXPRESS may be used as a final layer in residential areas, provided that ISOMAT BI-100 will be applied on its surface to increase the wear resistance, the resistance to detergents and to reduce water absorption.

Furthermore, FLOWCRET 1-10 EXPRESS (White) can be mixed with pigments based on iron oxides, in order to have a colored final surface.

Technical data

Form:	cementitious powder
Color:	grey, white
Water demand:	6,0-6,5 l/25 kg bag
Application thickness:	from 1mm to 10mm

Bulk density
of dry mortar: $1,40 \pm 0,15$ kg/l

Bulk density
of fresh mortar: $2,0 \pm 0,10$ kg/l

FLOWCRET 1-10 EPXPRESS Grey

Compressive strength acc. to EN 13892-2:
 • 24 hours: $11,00 \pm 1,00$ N/mm²
 • 7 days: $23,00 \pm 2,00$ N/mm²
 • 28 days: $35,00 \pm 3,00$ N/mm²

Flexural strength acc. to EN 13892-2:
 • 24 hours: $3,50 \pm 0,50$ N/mm²
 • 7 days: $6,00 \pm 1,00$ N/mm²
 • 28 days: $10,00 \pm 2,00$ N/mm²

Bond strength acc. to EN 13892-8:
 • 28 days: $1,70 \pm 0,50$ N/mm²

Wear resistance acc. to EN 13892-4 (BCA):
 • 28 days: AR4

Setting shrinkage acc. to EN 13872:
 • 28 days: $0,50 \pm 0,20$ mm/m

Reaction to fire: Euroclass A1_{fl}
(EN 13501-1)

Walkability: after 4 h

Successive layer (tiles): after 24 h

Pot life: 30-40 min at +20⁰C

FLOWCRET 1-10 EPXPRESS White

Compressive strength acc. to EN 13892-2:
 • 24 hours: $13,50 \pm 1,00$ N/mm²
 • 7 days: $17,50 \pm 2,00$ N/mm²
 • 28 days: $34,50 \pm 3,00$ N/mm²

Flexural strength acc. to EN 13892-2:
 • 24 hours: $4,00 \pm 0,50$ N/mm²
 • 7 days: $4,50 \pm 1,00$ N/mm²
 • 28 days: $9,00 \pm 2,00$ N/mm²

Bond strength acc. to EN 13892-8:
 • 28 days: $1,30 \pm 0,30$ N/mm²

Wear resistance acc. to EN 13892-4 (BCA):

- 28 days: AR6

Setting shrinkage acc. to EN 13872:

- 28 days: $0,40 \pm 0,20$ mm/m

Reaction to fire: Euroclass A1_{fl}
(EN 13501-1)

Walkability: after 4 h

Successive layer (tiles): after 24 h

Pot life: 30-40 min at +20°C

Directions for use

1. Substrate

The substrate must be dry, statically sufficient and also free of dust, grease, loose particles etc. Primarily, the surface is primed with the acrylic primer UNI-PRIMER. Product application follows once the primer has completely dried out (approx. after 2 hours). Primer consumption: 200-300 g/m².

2. Application

FLOWCRET 1-10 EXPRESS is gradually added into 6,0-6,5 l of water under continuous stirring, until a homogeneous, lump free, fluid mass is formed. The mixture is left about 2-3 minutes to settle and is then stirred again for 1 more minute. A low speed electric mixer (approx. 300 rpm) is recommended for mixing. The mortar is poured onto the primed substrate in one layer and is spread to the desired thickness with a large metal trowel, squeegee etc. As soon as the product has self levelled it must be rolled immediately with a suitable spiked roller to release all the air retained within its mass. For greater layer thickness, up to 30mm, it is recommended to use FLOWCRET 3-30 EXPRESS.

Consumption

Approx. 1,65 kg /m² /mm of layer thickness.

Packaging

FLOWCRET 1-10 EXPRESS is supplied in 25 kg paper bags.

Shelf-life - Storage

12 months from production date if stored in original, unopened packaging, in places protected from moisture and frost.

Remarks

- During application and initial setting/hardening of FLOWCRET 1-10 EXPRESS the surface must be protected from quick water loss due to the high temperature, U.V. radiation or wind.
- Do not add cement, gypsum, lime or other binders to the FLOWCRET 1-10 EXPRESS mix.
- Before the installation of parquet or vinyl tiles is necessary to measure the moisture content with a moisture meter.
- Temperature during application should be at least +5°C.
- Mixture that has started to harden should not be used.
- FLOWCRET 1-10 EXPRESS contains cement and reacts as alkaline with water, so it is classified as irritant.
- Consult the usage risks and safety advice written on the bag.

FLOWCRET 1-10 EXPRESS



FLOWCRET 1-10 EXPRESS GREY

ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece 08
EN 13813 CT-C30-F7-AR4 Cementitious screed material for use internally in buildings Reaction to fire: A1 _{fl} Release of corrosive substances: CT Water permeability : NPD Water vapour permeability: NPD Compressive strength: C30 Flexural strength: F7 Wear resistance: AR4 Sound insulation: NPD Sound absorption: NPD Thermal resistance: NPD Chemical resistance: NPD

FLOWCRET 1-10 EXPRESS WHITE

ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece 11
EN 13813 CT-C30-F7-AR6 Cementitious screed material for use internally in buildings Reaction to fire: A1 _{fl} Release of corrosive substances: CT Water permeability : NPD Water vapour permeability: NPD Compressive strength: C30 Flexural strength: F7 Wear resistance: AR6 Sound insulation: NPD Sound absorption: NPD Thermal resistance: NPD Chemical resistance: NPD

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.net e-mail: info@isomat.net

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

