

AQUAMAT-SR

Sulfate-resistant, brushable waterproofing slurry

Description	Technical data
<p>AQUAMAT-SR is a cement-based, brushable waterproofing slurry, suitable for waterproofing surfaces that come into contact with wastewater and groundwater containing sulfates. It has the following properties:</p>	<p>Form: cementitious powder</p>
<ul style="list-style-type: none"> • Total waterproofing against positive hydrostatic pressure up to 5 atm according to EN 12390-8. It can also withstand negative pressure. • High resistance to sulfates. • Simple and low cost application. • Perfect adhesion to substrates, such as concrete or masonry, even under negative pressure conditions. • Suitability for both horizontal and vertical surfaces. • Vapor permeability. • Protection of concrete from carbonation. • Suitability for application, in cases ranging from simple moisture to water under pressure. • Non-corrosive action on the steel of reinforced concrete. 	<p>Color: grey</p>
<p>Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked.</p>	<p>Water demand: 7.5-8.0 l/25 kg bag</p>
<p>Fields of application</p>	<p>Bulk density of dry mortar: 1.39 ± 0.05 kg/l</p>
<p>It is used for waterproofing walls and floors in wastewater treatment plants. Also suitable for restoring wall and floor surfaces that have been damaged by sulfates. It can be applied in cases ranging from simple moisture to water under pressure. It enables the internal waterproofing of underground spaces, as it can withstand negative pressure (water from the substrate side) without support, due to its perfect adhesion to the substrate.</p>	<p>Bulk density of fresh mortar: 1.90 ± 0.10 kg/l</p>
	<p>Adhesion (EN 1542): ≥ 1.0 N/mm²</p>
	<p>CO₂ permeability: > 50m (EN 1062-6 Method A, Sd > 50 m requirement)</p>
	<p>Capillary water absorption: 0.04 kg·m²·h^{0.5} (EN 1062-3: requirement EN 1504-2: w < 0.1)</p>
	<p>Vapor permeability: Sd < 5 m (EN ISO 7783-2, vapor-permeable Class I, Sd < 5 m)</p>
	<p>Pot Life: 1 h at +20°C</p>
	<p>Water penetration under positive hydrostatic pressure: no penetration (EN 12390-8, 3 days at 5 bar)</p>
	<p>Water penetration under negative hydrostatic pressure: no penetration (at 1.5 bar)</p>
	<p><u>Durability against:</u></p>
	<ul style="list-style-type: none"> • Rain: after approx. 4 h • Walking: after approx. 1 day • Water under pressure: after approx. 7 days • Backfill: after approx. 3 days

Directions for use

1. Substrate preparation

- The substrate should be clean, free of dust, oily or loose materials, etc.
- Water leaks should be plugged with AQUAFIX rapid-setting cement.
- Any cavities in concrete should be filled and smoothed out, using DUROCRET, RAPICRET or a cement mortar improved with ADIPLAST, after all loose aggregate has been removed and the surface has been well dampened.
- Starter bars and wooden molds should be cut to a depth of about 3 cm into the concrete and the holes should be filled, as described above.
- Existing construction joints are opened lengthwise in a V shape to a depth of about 3 cm and are filled as above.
- Corners, like the wall-floor junctions, should be filled and rounded with DUROCRET or a cement mortar improved with ADIPLAST (fillets having a triangular cross-sectional area with sides of 5-6 cm).
- In case of masonry walls, joints should first be carefully filled; otherwise, it is recommended to apply a cement mortar layer, previously improved with ADIPLAST.
- In case of internal basement waterproofing in old buildings, any existing plaster layer should be removed to a height of up to 50 cm above water level, before proceeding as above.
- Wherever forming flat surfaces is required (smoothing etc.), the use of DUROCRET, RAPICRET or a mortar improved with ADIPLAST is recommended.

2. Application

AQUAMAT-SR is gradually added to water under continuous stirring, until a uniform, viscous mixture is formed, suitable for brush application. The entire surface of the substrate should be well dampened, but without ponding water.

The material is applied in two or more layers, depending on the water load.

Layers thicker than 1 mm should be avoided, because the material may crack. Each new coating is brush-applied, after the previous one has dried. The freshly coated surface should be protected from high temperatures, rain and frost.

Elastification

In case of substrates subject to vibration or intense expansion-contraction, such as gypsum boards, chipboards, underfloor heating systems, terraces, balconies, swimming pools, etc., it is necessary to add 5-10 kg of ADIFLEX-B to 25 kg of AQUAMAT-SR, plus a quantity of water that depends on the desired workability, to improve its flexibility.

Consumption

Depending on the water load, minimum consumption and relative thickness should be as follows:

Water load	Minimum consumption	Minimum thickness
Moisture	2.0 kg/m ²	Approx. 1.5 mm
Water without pressure	3.0 kg/m ²	Approx. 2.0 mm
Water under pressure	3.5-4.0 kg/m ²	Approx. 2.5 mm

Packaging

25 kg bags.

Shelf life – Storage

12 months from production date if stored in its original, unopened packaging in a frost-free and dry place.

AQUAMAT-SR



Remarks

- In case of water under pressure, care should be taken so that pumping, which keeps the water level low, does not stop before AQUAMAT-SR has sufficiently hardened. About 7 days are needed.
- The structure bearing the waterproofing layer (wall, floor, etc.) should be properly designed, in order to be static enough to withstand the hydrostatic pressure.
- If there has been internal waterproofing and the floor is walkable, the floor surface that has been sealed with AQUAMAT-SR should be protected with a cement mortar layer.
- Temperature during the application should be at least +5°C.
- Due to cement content, the product reacts with water forming alkaline solutions, thus is classified as irritant.
- Please consult the safety instructions written on the packaging before use.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

14

EN 1504-2

Surface protection products
Coating

CO₂ permeability: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$

Adhesion: $\geq 1.0 \text{ N/mm}^2$

Reaction to fire: Euroclass A1

Dangerous substances comply with 5.3

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

Thessaloniki: 17th km. Thessaloniki - Ag. Athanasios

P.O. BOX 1043, 570 03 Ag. Athanasios

Tel. 2310 576 000 Fax: 2310 722 475

Athens: 57th km. National Road Athens-Lamia, 32011 Inofita

Tel. 22620 56 406 Fax: 22620 31 644

www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore, the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

