

ISOMAT BATH & KITCHEN

Premium anti-mold emulsion paint for interior use

Description

ISOMAT BATH & KITCHEN is a premium, anti-mold, matt emulsion paint for interior use. Thanks to its special fungicidal components, it drastically prevents the growth of mold and bacteria, making it ideal for areas with high moisture content, such as kitchens, bathrooms, ceilings, basements, etc. Features excellent surface coverage and opacity while offering very good workability and flow, as well as quick-drying time and outstanding resistance to frequent washing and aging. Provides strong adhesion to any kind of old or new substrate. Offers a beautiful matt finish. Almost odorless. Certified for its antibacterial activity according to ISO 22196: 2011.

Fields of application

ISOMAT BATH & KITCHEN is used for indoor applications especially on wet areas, on new or old surfaces, on ordinary building materials such as concrete, plaster, gypsum boards, etc.

Technical data

Colors:	white and thousands of colors (ISOMAT COLOR SYSTEM)
Type:	vinyl
Viscosity (Poise): (EN ISO 2884- 2)	115±5 KU
Volume solids content:	44±2 %
Dry film thickness: (EN ISO 2808)	32±3 µm
Density: (EN ISO 2811- 1)	1.46±0.03 kg/l
Bond strength: (EN ISO 4624)	≥ 2 N/mm ²
pH: (EN ISO 4316)	8-9.5 (+23°C)
Drying time: (EN ISO 9117)	1 h in 23°C (touch dry)
Recoat time: (EN ISO 9117)	3-4 h (23°C)

Vapor permeability: $S_d = 0.20 \pm 0.04$ m
(EN ISO 7783- 2: V_2 medium, $0.14 < S_d < 1.4$)

Capillary water absorption: $w = 0.04 \pm 0.02$ Kg/m²h^{0.5}
(EN ISO 1062- 3: W_3 low $w < 0.10$)

Antibacterial activity: Excellent, $R > 4.7$
Bacteria death >99.9%
(ISO 22196, test against Staphylococcus aureus and Escherichia coli, requirement $R > 2$)

VOC content = 11.6 g/l

Measurements acc. EN 13300

Gloss level: Dead Matt
(EN ISO 2813: < 5 at 85°)

Opacity: ≥ 93 %
(EN ISO 6504- 3)

Whiteness: ≥ 87 %
(EN ISO 6504- 3)

Wet Scrub Resistance: CLASS I
(EN ISO 11998: < 5 µm at 200 wash cycles).

Cleaning of tools:
Tools should be cleaned with water, immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of grease, loose particles, dust etc.

- Cracks or joints may be filled with ISOMASTIC-A acrylic sealant.
- Concrete imperfections should be repaired with DUROCRET polymer-modified mortar.
- Plastered wall may be repaired with UNICRET and UNICRET-FAST premixed mortars.
- For puttying surfaces, STUCCOCRET spatula putty should be used.

To recoat surfaces with mold growth, cleaning with ISOMAT's anti-mold cleaning agent CL-MOLD is required. After 24 hours, remove the mold traces, rinse with clean water and allow the surface to completely dry.

ISOMAT BATH & KITCHEN

The surface should be primed with the acrylic, micronized, water-based primer PRIMER CLASSIC, thinned up to 50% with clean water. PRIMER CLASSIC is also ideal to use for the stabilization of loose or crumbly substrates. Priming is not necessary on already painted surfaces as long as the old paint is sound.

2. Application

Before using, gently stir the content and apply as it is or thinned 5-10% with clean water. ISOMAT BATH & KITCHEN is applied in two coats with a roller, brush or airless gun. The second coat is applied once the first one has completely dried. Temperature during application and drying should be between +10°C and +35°C.

Coverage

ISOMAT BATH & KITCHEN covers 12 m²/l, on previously prepared surfaces.

Packaging

ISOMAT BATH & KITCHEN is supplied in buckets of 0.75 l, 3 l and 10 l.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory a, type WB is 30 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOMAT BATH & KITCHEN contains a maximum of 30 g/l VOC.

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu