

ISOMAT SL 17

Elastomeric liquid membrane for waterproofing under tiles

Description

ISOMAT SL 17 is a ready-to-use, waterborne, elastomeric, liquid waterproofing membrane for use under tiles. After hardening, it features high flexibility while being both waterproof and vapor-permeable.

Minimum application temperature:	+5°C
Recoat time:	1-2 h at +20°C
Tile fixing:	approx. after 6 h at +20°C
Hardening time:	≥ 6 h at +20°C

Fields of application

ISOMAT SL 17 is ideal for waterproofing surfaces in wet areas, such as bathrooms, showers, etc., (without forming seams or joints), before fixing ceramic tiles.

Suitable for all floor or wall surfaces made of concrete, plaster, gypsum boards, chipboards, etc. Yet, it should not be applied on surfaces subject to permanent water pressure.

Directions for use

1. Substrate

The substrate must be clean, free of grease, loose particles, dust, etc. Cavities should be repaired using PLANFIX putty. Priming follows using UNI-PRIMER special acrylic primer at a consumption of approx. 100-200 g/m², depending on the absorbency of the substrate.

2. Application

ISOMAT SL 17 is applied by brush or roller in two layers, after the primer has dried, and, if necessary, diluted with water up to 4% by weight. The second layer should be applied after the first one has dried. It can be also applied in one layer with a notched trowel of 3-4 mm notch size and flattened with a smooth trowel. In this way a uniform layer thickness is achieved.

ISOMAT SL 17 waterproofing membrane should be locally reinforced at joints and wall-floor junctions with fiberglass mesh (65 g/m²) or polyester fleece (30 g/m²).

Tools should be cleaned with water while ISOMAT SL 17 is still fresh.

Tiles should be fixed with a high performance, polymer-modified tile adhesive, such as ISOMAT AK 20, ISOMAT AK 22, ISOMAT AK 25, ISOMAT AK-ELASTIC, after ISOMAT SL17 has dried.

Technical data

Color:	grey
Density:	1.44 kg/l
Viscosity: (Brookfield R5/2)	100,000 mPa·s at +23°C
Elongation at break: (EN ISO 527)	215%
Dry film thickness: (EN ISO 2808) (Wet film thickness: 1000 µm, Solids content: 60%)	600 µm
Adhesion: (EN 1542, requirement for flexible systems with no traffic: 0.8 N/mm ²)	1.9 N/mm ²
Reaction to fire: (EN 13501-1)	Class F
Service temperature:	from -15°C to +80°C
Tensile strength: (EN ISO 527)	2.12 N/mm ²
Water vapor permeability coefficient (µ): (EN ISO 7783:2011)	19,300
Water impermeability: (DIN 1048)	7 atm
Capillary water absorption: (EN ISO 1062-3: W ₃ low, w < 0.10 Kg/m ² h ^{0.5})	0.01 Kg/m ² h ^{0.5}

Consumption

1.0-1.5 kg/m², depending on the substrate.

Packaging

ISOMAT SL 17 is supplied in buckets of 5 kg and 15 kg.

ISOMAT SL 17



Shelf life – Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory g, type WB is 30g/l (2010) for the ready-to-use product.

The ready-to-use product ISOMAT SL 17 contains max 9 g/l VOC.



2032

ISOMAT S.A.
17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios,
Greece

18

2032-CPR-10.11E

DoP No.: ISOMAT SL 17 / 1441-01

EN 1504-2

Surface protection products

Coating

Permeability to CO₂: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$

Adhesion: $\geq 0.8 \text{ N/mm}^2$

Reaction to fire: Euroclass F

Dangerous substances comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

