

Tile grout

Description

MULTIFILL 2-5 is a cement-based, colored tile grout. It offers high mechanical strength and color stability. Suitable for joint width 2-5 mm. It is classified as type CG2 WA tile grout according to EN 13888.

Fields of application

MULTIFILL 2-5 is used for pointing tile joints on walls or floors, for indoor and outdoor applications.

Technical data

Form:	cementitious powder
Colors:	24
Water demand:	6,50 l/25 kg bag
Bulk density of dry mortar:	1,25 ± 0,40 kg/l
Bulk density of fresh mortar:	1,60 ± 0,50 kg/l
Application temperature:	from +5°C to +35°C
Abrasion resistance: (EN 12808-2)	≤ 1000 mm ³
Compressive strength after:	
• 28 days:	40,00 N/mm ²
• 25 freeze-thaw cycles: (EN 12808-3)	40,00 N/mm ²
Flexural strength after:	
• 28 days:	6,00 N/mm ²
• 25 freeze-thaw cycles: (EN 12808-3)	5,00 N/mm ²
Drying shrinkage: (EN 12808-4)	≤ 2mm/m
Water absorption after:	
• 30 min:	≤ 2 g
• 240 min: (EN 12808-5)	≤ 5 g

Pot life:	at least 4 h at +20°C
Walkability:	after 10 h at +20°C

Directions for use

1. Substrate

The substrate covered with tiles should be perfectly clean. The joints should be carefully cleaned and dampened with a wet sponge.

2. Application

MULTIFILL 2-5 is added to water under continuous stirring, until a uniform paste is formed. A low revolution mixer is recommended for the mixing.

The mixture should be left about 3 minutes to settle and then slightly stirred again.

Spread the grout on to the joints, using a rubber float in a diagonal direction to the joints, in order to fill them completely. The excess material should be wiped after a while, using a wet sponge. Finally, the surface may be cleaned with a dry cloth.

Outdoors or at high temperatures repeated dampening is recommended after a few hours and when the grout has dried.

Consumption

The consumption of MULTIFILL 2-5 depends on the tile dimensions and the joint width. The following cases are mentioned indicatively (values in g/m²):

Tile Dimensions (cm)	Joint width			
	2 mm	3 mm	4 mm	5 mm
2 x 2 x 0,3	1.300	1.500	---	---
10 x 10 x 0,6	400	600	800	1.000
15 x 15 x 0,7	310	470	630	780
20 x 20 x 0,7	240	360	480	590
20 x 30 x 0,7	200	300	400	490
30 x 30 x 0,8	190	280	370	460

MULTIFILL 2-5



Packaging - Colors

MULTIFILL 2-5 is available in the following 24 colors, with the corresponding code No. and packaging (2 kg, 5 kg and 25 kg bags):

Color	2 kg	5 kg	25 kg
01 White	•	•	•
02 Black	•	•	
03 Grey	•	•	•
04 Pearl grey		•	
05 Light grey	•	•	•
06 Bahama beige	•	•	•
07 Redbrown		•	
08 Brown	•	•	
09 Light brown	•	•	
10 Dark grey	•	•	
11 Ivory		•	
12 Purple		•	
14 Cotto		•	
15 Manhattan grey		•	
16 Light ochre		•	
17 Anemone	•	•	
18 Pearl beige	•	•	
19 Mocha		•	
20 Maroon	•	•	
21 Caramel	•	•	
22 Magnolia		•	
24 Cinnamon		•	
30 Cement grey		•	
31 Ceramic		•	

Sets of realistic MULTIFILL samples are available.

Shelf-life - Storage

- Paper bags of 25 kg:
12 months from production date
- Plastic bags of 5 kg and 2 kg:
24 months from production date

All of the above are in effect if the product is stored in original unopened packaging, in places protected from moisture and frost.

Remarks

- MULTIFILL 2-5 contains cement and reacts as alkaline with moisture, so it is classified as irritant.
- Consult usage risks and safety advice written on the bag.

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.net e-mail: info@isomat.net

