

## Technical Datasheet

# POLYESTER FLEECE 60g

## Polyester fleece for reinforcing waterproofing layers

**Description – Fields of application**

PET crosslapped spunlace non-woven polyester fleece 60 g/m<sup>2</sup>, for local and total reinforcement of various waterproofing membranes (e.g. ISOFLEX, ISOFLEX-PU 500, AQUAMAT-ELASTIC, etc.) in case there are multiple severe cracks or localized cracks, at wall-to-floor junctions, corners, etc.

**Packaging**

1m x 50m rolls (50 m<sup>2</sup>), 10cm x 50m rolls.

**Storage**

Stored in its original, sealed packaging, protected from humidity and UV radiation.

**Technical data**

Weight:	60 g/m <sup>2</sup> (min. 54 – max. 66)
Thickness:	0.55 mm
Tensile strength: (EN ISO 13934-2)	
- Machine direction (MD):	160 N
- Cross direction (CD):	150 N
Elongation at break: (EN ISO 13934-2)	
- Machine direction (MD):	30-65%
- Cross direction (CD):	35-80%

**ISOMAT S.A.**  
BUILDING CHEMICALS AND MORTARS  
**HEADQUARTERS – FACTORY:**  
17<sup>th</sup> km Thessaloniki - Ag. Athanasios  
P.O. BOX 1043, 570 03 Ag. Athanasios  
Tel.: 2310 576 000 Fax: 2310 722 475  
**www.isomat.eu e-mail: support@isomat.eu**