

PRIMER ACRYL-S

Acrylic, solvent-based primer

Description

PRIMER ACRYL-S is an acrylic, solvent-based primer. It offers excellent bonding and high penetration. Penetrates and anchors to the porous of the substrate, waterproofing it while allowing it to breathe. Furthermore, it has the ability to harden weak substrates, such as brittle plasters, etc. It dries and is recoated rapidly and doesn't cause yellow stains to the finishing paints.

Fields of application

PRIMER ACRYL-S is recommended for use on new or old external porous surfaces that are to be covered with acrylic, waterproofing, emulsion and cement-based paints or silicone and acrylic plasters.

Technical data

Color: transparent
 Density: 0.85 kg/l
 Drying time: 1 h (touch dry)
 Recoat time: 2 h

Cleaning of tools:
 Clean the tools thoroughly with SM-21 of ISOMAT immediately after use.

Directions for use

1. Substrate

The surface to be primed must be dry and free of dust, grease, dirt, etc. while any imperfections on plaster should be restored.

2. Application

PRIMER ACRYL-S is applied in one layer thinned up to 100% with SM-21 of ISOMAT or with white spirit. For highly porous substrates use it undiluted.

Adjacent surfaces like windows and solvent-sensitive materials like polystyrene, sealants or mastics, etc., should be protected during application.

Consumption

About 10-15 m²/l per layer, depending on surface absorbency and thinning percentage.

Packaging

PRIMER ACRYL-S is available in containers of 1, 5, and 15 l.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging, in temperature between +5°C and +35°C. Protect from direct sunlight and frost.

Remarks

Temperature during application should be at among +10°C and +35°C.

Volatile organic compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory h, type SB is 750g/l (2010) for the ready-to-use product.

The ready-to-use product PRIMER ACRYL-S contains max 750 g/l VOC.

ISOMAT S.A.
 BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
 17th km Thessaloniki - Ag. Athanasios Road,
 P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
 Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu