

REOTOL-SPL

Concrete superplasticizer, type F

Description

REOTOL-SPL is a wide-range superplasticizer (ASTM C-494: Type A and F), offering the following advantages:

- When added during preparation of concrete, reduces the water required and the resulting water/cement ratio, thus significantly increasing both initial and final strength.
- When added into the ready-mixed concrete, increases slump from 1-4 cm to 18-22 cm, without additional water.
- Contributes to better hydration of cement.
- Facilitates compaction of concrete, reduces segregation and significantly improves workability and pumpability.
- Significantly reduces setting shrinkage, thus preventing cracks.
- Improves water impermeability.
- Does not have air entraining action.
- Is free of chlorides and other corrosive constituents.
- Does not have a retarding effect.
- Is compatible with all kinds of Portland cement.

Certified with the CE marking as high-range water reducing - concrete superplasticizing admixture, according to EN 934-2: T3.1 and T3.2, certificate number: 0906-CPR-02412007-01.

Fields of application

REOTOL-SPL is necessary for preparing high-strength concrete, exposed concrete, pumpable concrete, screeds for underfloor heating systems etc.

Technical data

Color:	dark brown
Density:	1.11 – 1.17 kg/l
pH:	8.20 ± 0.40
Maximum chloride content:	chloride free
Maximum alkali content:	≤ 4.0% by weight

Directions for use

REOTOL-SPL may be added:

- Into the mixing water during the preparation of concrete.
- Into the ready-mixed concrete, just before use. In this case, the concrete mixer truck drum should rotate for an additional 4-5 minutes, to achieve uniform dispersion into the concrete mass.

Dosage

As a type F superplasticizer: 0.2-1.4 kg per 100 kg of cement.

Packaging

REOTOL-SPL is available in plastic containers of 20 kg, in drums of 240 kg and in tanks of 1000 kg.

Shelf-life - Storage

18 months from production date, if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sun exposure and frost.

REOTOL-SPL



Remarks

- An excessive dose may cause retardation of setting time, without negatively affecting the final strength.

CE

0906

ISOMAT S.A.
17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

07

0906-CPR-02412007/01

EN 934-2:2009+A1:2012

DoP No.: REOTOL-SPL/1606-04

REOTOL-SPL

High Range Water Reducing/
Superplasticizing Admixture

EN 934-2: T3.1/3.2

Max chloride content: ≤ 0.1 % by weight

Max alkali content: ≤ 3.0 % by weight

Corrosive behaviour: contains components only
from EN 934-1:2008, Annex A.1

Dangerous substances: none

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

