

## Bonding agent - Two-component epoxy injection resin for cracks wider than 3mm

### Description

DUREBOND is a two-component epoxy system without solvents, offering excellent bonding to concrete and steel and high compressive and flexural strength, even when applied on damp substrates.

It complies with the requirements of ASTM C 881-90, Type II, Grade 2, Class B+C.

It is classified as a structural bonding agent for mortar or concrete and as a product for concrete injection, according to EN 1504-4 and EN 1504-5. Certificate Nr. 2032-CPR-10.11.

### Fields of application

DUREBOND is used as a bonding bridge for bonding fresh concrete or mortar to old hardened concrete, mortar or metallic surfaces.

DUREBOND is also used to repair concrete cracks wider than 3 mm by injection, in order to bond and restore the original monolithic structure.

DUREBOND is an ideal aid for installing and anchoring reinforcement rods into existing concrete elements.

### Technical data

Basis:	two-component epoxy resin
A-component color:	grey
B-component color:	brownish green
A+B color:	grey
Viscosity:	2.500 ± 500 mPa·s at +23°C
A-component density:	1.57 ± 0.03 kg/lit
B-component density:	1.04 ± 0.03 kg/lit
A+B density:	1.47 ± 0.03 kg/lit
Mixing ratio (A+B):	100:20 by weight

Pot life:	approx. 40 min at +20°C
Minimum hardening temperature:	+8°C
Final strength:	after 7 days at +23°C
Flexural strength: (DIN EN 196-1)	≥ 40.0 N/mm <sup>2</sup>
Tensile strength: (ASTM D 638)	29.9 N/mm <sup>2</sup>
Modulus of elasticity: (DIN 1048)	3,500 N/mm <sup>2</sup>
Water absorption: (ASTM D 570)	0.29% w/w after 24 h
Adhesion:	> 3.0 N/mm <sup>2</sup> (breaking point of concrete)

### EN 1504-4 as a structural bonding agent:

Adhesion for hardened concrete to hardened concrete and for fresh concrete to hardened concrete: (EN 12636)	Pass (fracture in the concrete)
---	---------------------------------

Shear adhesion strength for hardened concrete to hardened concrete: (EN 12615)	8.8 N/mm <sup>2</sup>
--	-----------------------

Compressive strength: (EN 12190)	≥ 90.0 N/mm <sup>2</sup>
----------------------------------	--------------------------

Shrinkage: (EN 12671-1)	0.05%
-------------------------	-------

Workability: (EN ISO 9514)	35 minutes at +20°C
----------------------------	---------------------

Sensitivity to water: (EN 12636)	Pass
----------------------------------	------

Modulus of elasticity in compression: (EN 13412)	3,470 N/mm <sup>2</sup>
--	-------------------------

Coefficient of thermal expansion: (EN 1770)	52 X 10 <sup>-6</sup>
Glass transition temperature: (EN 12614)	≥ 73 °C
Reaction to fire: (EN 13501-1)	Euroclass E
Durability: (EN 13733)	Pass *

*\*The compressive shear load at failure after exposure to thermal cycling shall not be less than the lowest tensile strength of the bonded or the original concrete.*

EN 1504-5, as an injection product for concrete:

Adhesion by tensile bond strength: (EN 12618-2)	5.9 N/mm <sup>2</sup>
Adhesion by slant shear strength: (EN 12618-3)	Monolithic failure
Volumetric shrinkage: (EN 12617-2)	1.5 %
Glass transition temperature: (EN 12614)	≥ 73 °C

Workability:

- Minimum crack width: 3 mm.
  - Suitable for injection into dry and slightly damp medium.
- (EN 12618-2)

Durability: (EN 13733)	Pass *
---------------------------	--------

*\*The compressive shear load at failure after exposure to thermal cycling shall not be less than the lowest tensile strength of the bonded or the original concrete.*

Corrosive behavior:	No
---------------------	----

Cleaning of tools:  
Tools should be cleaned with SM-12 solvent or water, immediately after use.

## Directions for use

### 1. Substrate preparation

The application surface should be:

- Dry and durable.
- Free of materials that prevent bonding, e.g. dust, grease, loose particles etc. and without standing water.

### 2. Mixing of the components

Components A (resin) and B (hardener) are packed in two separate containers, having the correct predetermined mixing proportion by weight. The whole quantity of comp. B is added into comp. A and they are mixed for about 5 minutes, using an appropriate hand tool (e.g. small trowel) or with a low speed mixer (300 rpm). It is important to stir the thoroughly mixture near the sides and bottom of the container, to achieve uniform dispersion of the hardener.

In case less quantity is required (than the one available in the package), 5 parts by weight of comp. A and 1 part by weight of comp. B should be poured into a clean container and mixed as above.

### 3. Application – Consumption

#### A) Bonding of fresh concrete to hardened concrete

DUREBOND is applied by roller or brush in one layer.

Consumption: Approx. 0.6 kg/m<sup>2</sup>.

Then, the concrete or mortar is applied, while DUREBOND is still fresh (within 90 min from application, at +20°C).

#### B) Resin injections

1. Remove any existing plaster on either side of the crack and thoroughly clean the concrete substrate.

2. Seal the crack using EPOMAX-EK and fix injection nozzles along the crack, approx. every 20 cm, with the same product.
3. After EPOMAX-EK has hardened, start injecting DUREBOND into the crack, by pressing the material through the nozzles, following this procedure:
  - a) Place the resin outflow tube (e.g. spirit level tube) in the first nozzle. For a horizontal crack, start from one end. For a vertical crack, start from the lowest nozzle.
  - b) Inject into the first nozzle by adjusting the outflow valve of the compression boiler, until DUREBOND begins to flow out of the adjacent nozzle or until no further pressure can be applied.
  - c) Cap the first nozzle and continue the injection through the next nozzle.
  - d) Repeat this process until the entire length of the crack has been treated. Allow the material to cure and the next day, remove (break) the beetling nozzles and restore plastering.

Consumption: To fill an empty space of 1lit, approx. 1.5 kg of DUREBOND is required.

### C) Anchoring

Open holes of a bigger diameter than the rods to be installed and as deep as possible. For vertical elements, holes should not be opened horizontally, but in a dipping direction (downwards). Blow compressed air to clean the holes. Pour DUREBOND into the holes in a quantity slightly bigger than necessary, so that putting the rod inside the hole will cause the material to flow out.

Consumption: To fill an empty space of 1lit, approx. 1.5 kg DUREBOND is required.

### Packaging


DUREBOND is supplied in packages (A+B) of 1 kg and 4 kg with components A and B having a fixed proportion by weight.


### Shelf-life - Storage

12 months from production date, if stored in original sealed packaging, in areas protected from humidity and direct sun exposure. Recommended storage temperature: between +5°C and +35°C.

### Remarks

- The workability of epoxy materials is affected by temperature. The ideal temperature of application is between +15°C and +25°C, for which the product obtains optimal workability and curing time. Room temperature below +15°C will expand the curing time, while temperatures above +30°C will reduce it. It is recommended to mildly preheat the product in the winter, and store the product in a cool room before application in the summer.
- After hardening, DUREBOND is totally safe for health.
- Before application, consult the directions for safe use and precautions written on the package.

 <b>2032</b>
<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece <b>10</b>
<p style="text-align: center;"><b>2032-CPR-10.11</b></p> <p style="text-align: center;">EN 1504-4</p> <p style="text-align: center;">DoP No: DUREBOND/1809-02</p> <p style="text-align: center;">Structural bonding product for bonded mortar or concrete for uses other than low performance requirements</p> <p>Adhesion: Fracture to concrete</p> <p>Shear Strength: <math>\geq 6.0 \text{ N/mm}^2</math></p> <p>Compressive strength: <math>\geq 30.0 \text{ N/mm}^2</math></p> <p>Shrinkage/expansion: <math>\leq 0.1\%</math></p> <p>Workability: 35 minutes at +20 °C</p> <p>Sensitivity to water: pass</p> <p>Modulus of elasticity: <math>\geq 2,000 \text{ N/mm}^2</math></p> <p>Coefficient of thermal expansion: <math>\leq 100 \times 10^{-6}</math> per K</p> <p>Glass transition temperature: <math>\geq 40 \text{ °C}</math></p> <p>Reaction to fire: Euroclass E</p> <p>Durability: Pass</p> <p>Dangerous substances: comply with 5.4</p>

 <b>2032</b>
<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece <b>10</b>
<p style="text-align: center;"><b>2032-CPR-10.11</b></p> <p style="text-align: center;">EN 1504-5</p> <p style="text-align: center;">DoP No: DUREBOND/1809-02</p> <p style="text-align: center;">Concrete injection product                  U (F1) W (30) (1/2) (8/35) (1)                  Force transmitting and filling of cracks                  3 mm                  Dry and damp cracks                  8 °C to 35 °C</p> <p>Adhesion by tensile bond strength: cohesive failure in substrate</p> <p>Adhesion by slant shear strength: monolithic failure</p> <p>Volumetric shrinkage: <math>&lt; 3.0 \%</math></p> <p>Glass transition temperature: <math>\geq 40 \text{ °C}</math></p> <p>Workability</p> <p>Crack width from 3 mm</p> <p>Moisture state of the crack: dry and damp</p> <p>Durability: Pass</p> <p>Corrosion behavior: deemed to have no corrosive effect</p> <p>Dangerous substances: comply with 5.4</p>

**ISOMAT S.A.**  
 BUILDING CHEMICALS AND MORTARS  
**MAIN OFFICES - FACTORY:**  
 17th km Thessaloniki - Ag. Athanasios Road,  
 P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,  
 Tel.: +30 2310 576 000, Fax: +30 2310 722 475  
[www.isomat.net](http://www.isomat.net) e-mail: [info@isomat.net](mailto:info@isomat.net)