

Tile adhesive primer

Description

One-component adhesion primer based on acrylic resins. It is used for the preparation of smooth, absorbent and non-absorbent substrates before the application of cement-based adhesives for tiles, natural or synthetic stones, etc.

Fields of application

ISOMAT AK-PRIMER can be applied as an adhesion primer on various substrates, such as old tiles, marble, natural stones, smooth cement-based industrial floorings, wooden, metal or rigid PVC floorings, etc.

Technical data

Form:	polymer emulsion
Color:	light purple
Density:	1.00 kg/l
pH:	9
Successive layer:	after 1 h at +20°C

Directions for use

1. Substrate preparation

The surface to be primed must be dry and free of dust, grease, dirt etc.

2. Application

In case of non-absorbent substrates, ISOMAT AK-PRIMER is poured directly from the container onto the substrate and spread with a roller or brush in one layer. If after applying the first coating, the surface has not been completely covered with the material, then a second layer should be applied, after the first one has dried. The adhesive may be applied one hour after priming and while ISOMAT AK-PRIMER is still tacky.

In case of absorbent substrates, ISOMAT AK-PRIMER is diluted with pure water (at a ratio of 1:0.5 up to 1:1), depending on the substrate absorptivity.

Then, ISOMAT AK-PRIMER is uniformly applied on the substrate with a roller or brush. The adhesive may be applied after the primer has dried.

Consumption

100-200 g/m², depending on the substrate absorptivity.

Packaging

Containers of 1 kg and 5 kg.

Shelf-life - Storage

Shelf-life in sealed containers is 12 months from production date, in dry and frost-free conditions.

Remarks

- The application temperature should range from +5°C to +35°C.
- The maximum period allowed for overlaying is 12 hours (at +20°C). Once this period has elapsed, a new layer of ISOMAT AK-PRIMER should be applied, before the application of the tile adhesive.

Volatile Organic Compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory h, type WB is 30g/l (2010) for the ready-to-use product. The ready-to-use product ISOMAT AK-PRIMER contains a maximum of 30 g/l VOC.

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.net e-mail: info@isomat.net