

Fibre-reinforced adhesive for thermal insulation boards

Description

ISOMAT AK-THERMO is a fibre-reinforced cement-based adhesive, enriched with polymers (resins). It provides high initial and final adhesive strength, elasticity and resistance to moisture.

It is classified as a GP CS IV W2 rendering mortar according to EN 998-1 and as a C2E adhesive according to EN 12004.

Fields of application

ISOMAT AK-THERMO is used in combination with MARMOCRET PLUS and MARMOCRYL renders as a system for creating external thermal insulated facades. It is suitable for fixing thermal insulation boards of extruded or expanded polystyrene, mineral wool, polyurethane, cork, etc. on facades made of concrete, render, or masonry.

Moreover, when reinforced with fibreglass mesh and applied on the exterior side of fixed thermal insulation boards, it constitutes the ideal substrate for the subsequent render layer.

Technical data

Form:	cementitious mortar
Color:	white
Water demand:	6,25 l/25 kg bag
Bulk density of dry mortar:	1,40 ± 0,10 kg/l
Bulk density of fresh mortar:	1,55 ± 0,10 kg/l
Application temperature:	from +5°C to +35°C
Pot life:	at least 6 h
Open time:	at least 20 min
Compressive strength:	≥ 14,50 N/mm ²
Flexural strength:	≥ 5,00 N/mm ²

Adhesion on concrete (28 days):	≥ 2,00 N/mm ²
Adhesion on XPS (28 days):	≥ 0,35 N/mm ²
Adhesion on EPS (28 days):	≥ 0,10 N/mm ² (EPS failure)
Capillary water absorption:	≤ 0,2 kg/m ² min ^{0,5}
Thermal conductivity (λ _{10,dry}):	0,43 W/mK
Water vapour permeability coefficient (μ):	20

Directions for use

1. Substrate

The surface to be covered with boards should be free of dust, grease, loose particles, paints etc. It is recommended that it is dampened before application.

2. Application

As adhesive:

ISOMAT AK-THERMO is gradually added into water under continuous stirring until a homogeneous paste is formed. A low revolution mixer is recommended for mixing. The mixture should be left for about 10 minutes to rest and then should be re-stirred a bit.

On smooth substrates the adhesive is spread on the surface and combed using a notched trowel in order to be uniformly applied on the whole of the surface.

On uneven substrates the adhesive is applied with a trowel around the perimeter of the thermal insulation board and in selected spots in the center.

Next, the thermal insulation boards are fixed by pressing them on the desired position.

As reinforced mortar:

Initially the material is applied with a notched trowel in a maximum thickness of 3 mm. On the still fresh layer the fiberglass mesh is placed and pressed with the trowel to get fully encased in the adhesive. Finally, the surface is smoothed out and the excess adhesive is removed.

Consumption

As adhesive: 2,0-4,0 kg/m², depending on the trowel's notch size and the nature of the substrate.

As reinforced mortar: approx. 1,5 kg/m²/mm.

Packaging

ISOMAT AK-THERMO is supplied in paper bags of 25 kg.

Shelf-life - Storage

12 months from production date if stored in original, unopened packaging, in places protected from moisture and frost.

Remarks

- ISOMAT AK-THERMO contains cement and reacts as alkaline with moisture, so it is classified as irritant.
- Very porous surfaces such as aerated concrete, gypsum boards, chipboards etc. must be primed first with the acrylic primer UNI-PRIMER.
- Consult usage risks and safety advice written on the bag.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

11

EN 998-1

**General purpose rendering mortar (GP)
for external use**

Reaction to fire: Class A1

Adhesion: 2,0 N/mm² – FP: A

Water absorption: W2

Water vapour diffusion coeff.: μ 20

Thermal conductivity: (λ_{10,dry}) 0,43 W/mK

Durability (against freeze/thaw): evaluation based on provisions valid in the intended place of use of the mortar

ISOMAT AK-THERMO



11

ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

EN 12004

Improved, cementitious adhesive for tiling with
extended open time

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.net e-mail: info@isomat.net

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

