

ROOF-TOP

Roofing membrane for ventilated roofs

Description	Technical data
<p>The waterproofing membrane ROOF-TOP can be installed on ventilated (cold) roofs onto the sheeting. Alternatively, it can be used on cold roofs without sheeting. In that case, the membrane should be placed onto the rafters or the counter battens that encompass the thermal insulation - either stretched or sagging. The membrane is also used in (cold) roofs made of reinforced concrete and is placed onto the counter battens.</p> <p>The waterproofing membrane consists of a layer of oxidized bitumen that forms the absolute insulation against water, humidity and vapor and is covered with thin, protective polyethylene films.</p> <p>The membrane has minimum vapor permeability ($S_d > 100$ m) due to its bituminous composition, so it is recommended that the joints of successive leaves should not be sealed in order to allow vapor (not water) to pass through and let the roof breathe. Moreover, the membrane is very easily mounted, as well as tear resistant because of its low weight, satisfactory flexibility and great tensile strength.</p> <p>In case a vapor-barrier is required, ROOF-TOP is ideally combined with the roofing membrane – vapor barrier DELTA-REFLEX.</p>	<p>Material: 3 layers – modified bitumen layer between thin polyethylene films</p> <p>Reinforcement: non-woven polyester</p> <p>Tensile strength (EN 12311-1):</p> <ul style="list-style-type: none"> • Longitudinal: 500 N/5 cm • Transverse: 300 N/5 cm <p>Elongation (EN 12311-1):</p> <ul style="list-style-type: none"> • Longitudinal: 35% • Transverse: 35% <p>Tear resistance (EN 12310-1):</p> <ul style="list-style-type: none"> • Longitudinal: 120 N • Transverse: 150 N <p>Resistance to static load (EN 12730):</p> <ul style="list-style-type: none"> • Method A: 20 kg • Method B: 20 kg <p>Impermeability(EN 1928): waterproofing membrane</p> <p>Vapor-permeability $S_d > 100$ m</p> <p>Resistance to temperature changes: -40°C up to +90°C</p> <p>Weight: Available in two types: 650 & 800 gr/m²</p>

Packaging

Rolls of 1m x 30m (30 m²) each.

ISOMAT S.A.
 BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
 17th km Thessaloniki - Ag. Athanasios Road,
 P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
 Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

