

ISOMATAK 22

Ekstra fleksibilni, polimer-modifikovani lepak visokih performansi za sve vrste pločica, čak i na podlogama podložnim vibracijama

Opis

ISOMAT AK 22 je visoko kvalitetni polimer-modifikovani lepak za pločice na cementnoj bazi. Pruža visoku početnu i finalnu čvrstoću, adheziju, otpornost na vlagu i elastičnost. Apsolutno je neklizajući (faktor klizanja pločice je nula) i povećano mu je vreme otvorenosti za rad. Klasifikovan je kao C2 TE S1 lepak prema EN 12004.

Primena

ISOMAT AK 22 je namenjen za lepljenje upijajućih i neupijajućih pločica, prirodnog kamena, dekorativne cigle, velikih ploča, itd., na podne površine različitih tipova, pogotovu tamo gde se zahteva izuzetno visoka adhezija, elastičnost i otpornost na vlagu (npr. prepokrivanje starih pločica, podovi sa podnim grejanjem, metalne površine, bazeni za plivanje, gips-ploče i sl.). Pogodan je i za unutrašnju i za spoljašnju upotrebu.

Tehnički podaci

| | |
|--|--------------------------|
| Oblik: | cementni malter |
| Boje: | siva, bela |
| Potrošnja vode: | 7,75 l/25 kg |
| Temperatura primene: | od +5°C do +35°C |
| Debljina nanošenja: | do 15 mm |
| Upotrebljivost: | minimum 6 h |
| Otvoreno vreme za rad: | minimum 30 min |
| Otvoreno vreme za manje popravke: | minimum 30 min |
| Klizanje: | ≤ 0,5 mm |
| Adhezionna sila posle: | |
| • 28 dana: | ≥ 1,90 N/mm ² |
| • zagrevanja +70°C: | ≥ 1,90 N/mm ² |
| • potapanja u vodu: | ≥ 1,50 N/mm ² |
| • smrzavanje-odmrzavanje (25 ciklusa): | ≥ 1,50 N/mm ² |
| Fugovanje zidova: | posle 3-8 h |

Fugovanje podova: posle 24 h

Otpornost na temperature: od -30°C do +90°C

Sposobnost deformacije (EN 12004-2): > 2,5 mm

Sva merenja su izvršena u skladu sa standardom EN 12004-2.

Uputstvo za upotrebu

1. Podloga

Površina koju tretiramo mora da bude čista, bez prašine, masnoće, boje, trošnih materijala, itd. Neophodno je kvašenje podloge pre nanošenja materijala.

2. Nanošenje

ISOMAT AK 22 se postepeno dodaje u vodu uz stalno mešanje, dok se ne formira jednolična pasta. Može da se koristi mikser sa niskim brojem obrtaja.

Mešavinu treba ostaviti oko 5 minuta da odleži, pa je opet promešati. Lepak za pločice se razvlači ("češlja") po podlozi pomoću zupčaste špantle, kako bi se ravnomerno rasporedio po celoj površini. Pločice se postavljaju utiskivanjem na željenu poziciju. Nanešeni lepak treba pokriti pločicama unutar perioda od 30 minuta da bi se izbeglo formiranje "pokožice", tj. pre nego što namaz lepka počne da se steže.

Potrošnja

1,5-4,0 kg/m², zavisno od veličine zubaca na špantli i vrste podloge.

Pakovanje

Dostupan je u:

- Plastičnim kesama od 5 kg u sivoj i beloj boji
- Papirnim kesama od 15 kg u beloj boji
- Papirnim kesama od 25 kg u sivoj i beloj boji

ISOMAT AK 20

Rok upotrebe - Skladištenje


- Papirna vreća od 25 kg i 15 kg:
12 meseci od datuma proizvodnje
- Plastične vreće od 5 kg:
18 meseci od datuma proizvodnje

Svi gore navedeni rokovi trajanja su važeći ukoliko se proizvod skladišti u originalnom pakovanju, na mestima zaštićenim od vlage i mraza.

Napomene


- ISOMAT AK 22 sadrži cement i sa vodom reaguje alkalno, tako da je klasifikovan kao iritant.
- Veoma porozne površine kao što su gas-beton, gips-ploče, iverica, itd. Treba prethodno prajmerisati akrilnim prajmerom UNI-PRIMER.
- Pažljivo proučite upozorenja i uputstva ispisana na ambalaži proizvoda.

ISOMAT AK-22 GREY

| | |
|---|-----------------------|
|  | |
| ISOMAT D.O.O. PRHOVACKA BB 22310 SIMANOVCI SERBIA 11 | |
| EN 12004:2007+A1:2012 DoP No.: ISOMAT AK-22 GREY/1066-01 NB: 2032 Improved deformable cementitious adhesive with reduced slip and extended open time, for internal and external tiling. | |
| Reaction to fire | Class E |
| Release of dangerous substances | See MSDS |
| Bond strength, as: | |
| - initial tensile adhesion strength | ≥ 1 N/mm ² |
| Durability, for | |
| - tensile adhesion strength after heat ageing | ≥ 1 N/mm ² |
| - tensile adhesion strength after water immersion | ≥ 1 N/mm ² |
| - tensile adhesion strength after freeze thaw cycles | ≥ 1 N/mm ² |

ISOMAT AK 20

ISOMAT AK-22 WHITE

| | |
|--|-----------------------|
|  | |
| ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece 08 | |
| EN 12004:2007+A1:2012 DoP No.: ISOMAT AK-22 WHITE/1006-02 NB: 2032 Improved deformable cementitious adhesive with reduced slip and extended open time, for internal and external tiling. | |
| Reaction to fire | Class E |
| Release of dangerous substances | See MSDS |
| Bond strength, as: | |
| - initial tensile adhesion strength | ≥ 1 N/mm ² |
| Durability, for | |
| - tensile adhesion strength after heat ageing | ≥ 1 N/mm ² |
| - tensile adhesion strength after water immersion | ≥ 1 N/mm ² |
| - tensile adhesion strength after freeze thaw cycles | ≥ 1 N/mm ² |

ISOMAT S.A.
 BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
 17th km Thessaloniki - Ag. Athanasios Road,
 P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
 Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.rs e-mail: info@isomat.rs