

Corrosion inhibiting impregnation

Description

FERROSEAL-CSI is an aqueous solution with high penetrating properties. It is a surface applied corrosion inhibitor, designed for use as an impregnation of steel reinforced concrete. It has the ability to migrate through concrete and to form a protective layer on the surface of the reinforcement steel.

- It extends the working life of the structure.
- It inhibits the start of corrosion in new structures.
- It reduces the corrosion rate on existing structures.
- It does not change the appearance of the concrete structure.
- It does not alter the water vapour diffusion properties of concrete.
- It is easy to apply.

Fields of application

FERROSEAL-CSI is used as a precautionary corrosion protection of steel reinforced concrete structures above and below ground. Also it is ideal for repairs of reinforced concrete. Furthermore it is suitable as an anticorrosive protection for structures of reinforced concrete that are exposed on aggressive environment such as bridges, aqueducts etc.

Technical data

Form:	liquid
Color:	transparent
Density:	1,02 kg/l
pH:	11

Directions for use

1. Substrate

The substrate must be dry, sound and free of dust, grease, loose materials, paints etc. If cleaning is required it is recommended to be done by water blasting. The surface must be dry before the application of FERROSEAL-CSI.

Damaged concrete must be first repaired, (removal of loose concrete, restoration of the reinforcement, reprofiling) by using the proper repairing products.

2. Application

FERROSEAL-CSI is ready to use and should not be diluted with water. It is applied on the substrate by spraying, by brush or by roller, until the surface is fully saturated. Usually 3 to 5 layers must be applied to achieve the minimum required consumption. Each layer is applied after the previous one has dried. To increase the migration speed of FERROSEAL-CSI inside concrete, the surface can be sprayed with water 1-2 times after 2-3 days of the application. In case the treated surface with FERROSEAL-CSI will be later covered by paint or by a repairing mortar, this can be done if it has been previously water blasted (not earlier than 2 days after the application of FERROSEAL-CSI).

Consumption

Approximately 0,5 kg/m². To achieve adequate protection of the steel reinforcement the consumption should not be less than 0,3 kg/m².

Packaging

Containers of 1, 5 and 20 kg.

FERROSEAL-CSI



Shelf-life - Storage

24 months from production date if stored in original, unopened packaging, in places protected from moisture and frost.

Remarks

- Temperature during the application should be at least +5°C.
- The following materials should be protected from contact with FERROSEAL-CSI: silicone sealants, PVC, epoxy and polyurethane layers, metallic surfaces (aluminium, copper, galvanized steel), wood, marbles and natural stones.
- Do not use it on surfaces saturated with water.
- Consult the safety instructions written on the packaging.

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.net e-mail: info@isomat.net

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

