

ISOLAC-AQUA

Premium quality, water-based, enamel paint

Description

Premium quality, new generation, water-based, enamel paint for wooden surfaces. It is suitable for both indoor and outdoor use. ISOLAC-AQUA is characterized by high flexibility and coverage. It has excellent resistance to weather, aging and frequent washing and therefore it does not turn yellow. It has strong adhesion and is suitable for repainting surfaces coated with water-based or solvent-based enamel paints. It is almost odorless, it has excellent workability and dries quickly. It is available in gloss (ISOLAC-AQUA GLOSS) and in satin finish (ISOLAC-AQUA SATIN).

Fields of application

ISOLAC-AQUA is used for indoor or outdoor applications, on new or old wood surfaces.

Technical data

Colors:	white and 1950 selected colors (ISOMAT COLOR SYSTEM)
Type:	water-based enamel paint
Density:	1.25 kg/l (GLOSS), 1.30 kg/l (SATIN)
pH:	8-9 at +23°C
Opacity:	min 97%
Whiteness:	min 95%
Capillary water absorption:	0.05 kg/m ² h ^{0.5}
Bond strength:	2.0 N/mm ²
Viscosity (Poise):	15-20
Drying time:	1 h (to the touch)
Recoating in:	6 h

Cleaning of tools:

Remove as much paint as possible from the used tools before cleaning. Clean the tools thoroughly with water and detergent immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of grease, loose particles, dust etc., while any imperfections should be rubbed down with sandpaper. It should then be primed with ISOLAC PRIMER AQUA, thinned up to 5-10% with clean water for application by brush or by roller and up to 20-30% for airless spray application.

2. Application

Before using ISOLAC-AQUA, slightly stir its content and apply it in two layers, thinned by 5-10% with clean water for application by brush or roller, and up to 20-30% for airless spray application.

The second coat is applied after the first coat has completely dried. Temperature during application and drying of the paint should be between +10°C and +35°C.

Coverage

ISOLAC-AQUA covers 12 m²/l per coat, on previously prepared surfaces.

Packaging

ISOLAC-AQUA is available in 0.75 and 2.5 l containers.

ISOLAC-AQUA

Shelf-life - Storage

24 months from production date, if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sun exposure and frost.

Volatile Organic Compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory d, type WB is 130 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOLAC-AQUA contains a maximum of 130 g/l VOC.

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

