Technical Datasheet

MARMOCRYL SILICONE-SILICATE Fine



Silicone-Silicate, pasty, ready-to-use render Smooth finish • White or colored • Water-repellent

Description

MARMOCRYL SILICONE-SILICATE Fine is a ready-to-use, pasty, white or colored silicate render with special silicone additives. It consists of aggregates of special particle size that form a smooth decorative surface. It offers the following benefits:

- High elasticity and excellent bonding to the substrate.
- Water-repellency.
- Excellent vapor permeability and thus maximum breathing of the building.
- · No need for facade painting.
- Resistance to alkalis, according to DIN 18556.
- Crack prevention, unlike ordinary cementlime renders.
- Simplified and fast application.
- Suitability for interior and exterior application.

Certified with the CE marking, according to EN 15824.

Fields of application

MARMOCRYL SILICONE-SILICATE Fine is used as the finishing coat of rendering works, in order to create a white or colored, water-repellent smooth finish surface (thin layer). It can be applied on all kinds of building materials, like render, concrete, cement boards, gypsum boards, etc. It is suitable for exterior and interior applications and replaces the final render coat.

Due to its high elasticity and excellent bonding to the substrate, it is also an ideal final layer for external, thermally insulated facades.

Technical data

Form: pasty

Colors: white and 1024

selected color

(ISOMAT

COLOR SYSTEM)

Density: $1.80 \pm 0.03 \text{ kg/l}$

Water vapor permeability: V1

(EN ISO 7783-2, V1: High Sd<0.14m)

Water permeability W2

(EN 1062-3, W2: Medium 0.1<w< 0.5 kg/m²h^{0.5})

Adhesion: 0.4 MPa

(EN 1542)

Thermal conductivity $\lambda=0.7 \text{ W/(m} \cdot \text{K)}$

(EN 1745)

Reaction to fire Euroclass C

(EN 13501-1)

Drying time: 4-6 h (23°C and

50% R.H.)

Cleaning of tools:

Tools should be cleaned with water, immediately after use.

Available Types

Depending on the particle size of aggregates, MARMOCRYL SILICONE-SILICATE Fine is available in the following types:



MARMOCRYL SILICONE-SILICATE Fine

Туре	Thickness of application
MARMOCRYL SILICONE- SILICATE Fine 1 mm	approx. 1 mm
MARMOCRYL SILICONE-	approx.
SILICATE Fine 1.5 mm	1.5 mm
MARMOCRYL SILICONE-	approx.
SILICATE Fine 2 mm	2 mm

Consumption

Approx. 1.8 kg/m²/mm of render thickness.

Directions for use

1. Substrate preparation

The substrate must be dry and free of dust, oily or loose materials, etc. It should be primed with the special primer SILICONE-PRIMER. Smooth or non absorbent surfaces should be primed with PL-BOND. MARMOCRYL SILICONE-SILICATE Fine is applied, after the primer has dried.

2. Application

MARMOCRYL SILICONE-SILICATE Fine should be thoroughly stirred before application. This should be done with slow circular movements to avoid creating bubbles in the mass of the material. The render is applied by hand, using a smooth, stainless, metal trowel, or with a rendering machine.

While still fresh, the render is treated (pressed) with a plastic trowel. Working time depends on the substrate absorptivity and ambient temperature.

Packaging

MARMOCRYL SILICONE-SILICATE Fine is supplied in 25 kg plastic containers.

Shelf-life - Storage

18 months from production date, if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sun exposure and frost.

Remarks

- The natural aggregates used in the render can cause slight differences in color. For this reason and in order to achieve a uniform color result, it is recommended to use products of the same batch or to mix products of different batches. Moreover, the final color may be affected by the substrate, as well as the ambient temperature and humidity.
- Temperature during application should be between +5°C to +35°C.
- While still fresh, MARMOCRYL SILICONE-SILICATE Fine should be protected from high temperatures, rain and frost.
- Consult the directions for safe use and precautions written on the package.

Volatile Organic Compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory c, type WB is 40 g/l (2010) for the ready-to-use product.





MARMOCRYL SILICONE-SILICATE Fine

The ready-to-use product MARMOCRYL SILICONE-SILICATE Fine contains a maximum of 40 g/l VOC.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

13

EN 15824

External render based on organic binder

DoP No.: MARMOCRYL SILICONE – SILICATE

FINE / 1412-03

Water vapor permeability: V1

Water absorption: W2 Adhesion: 0.4 MPa

Durability: NPD

Thermal conductivity: $\lambda = 0.7 \text{ W/(m} \cdot \text{K)}$

Reaction to fire: Euroclass C

ISOMAT S.A. BUILDING CHEMICALS AND MORTARS MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road, P.O. BOX 1043, 570 03 Ag. Athanasios, Greece, Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: info@isomat.eu

