

ISOCURE-SB

Acrylic sealing and anti-evaporation agent for concrete

Description

Solvent-based polymer emulsion with acrylic resins applied to freshly casted concrete to prevent rapid evaporation of mixing water from fresh concrete surfaces. Protects fresh or hardened concrete as well.

Offers the following advantages:

- Significant water loss reduction and high moisture retention.
- Effective curing and sealing of concrete surfaces.
- High abrasion resistance.
- Excellent adhesion to old and new concrete.
- Water-repellency and protection against water penetration.
- Shrinkage reduction during concrete setting.
- Hairline crack resistance.
- Surface anti-dust protection after concrete setting.
- Compatible with surface hardeners, such as EXTRA-TOP.
- Suitable for indoor and outdoor use.
- Easy application by spray or roller.

Certified according to EN 13813 and classified as composite decking, category SR-B2.0-AR0.5. ISOCURE-SB complies with the requirements of ASTM C 309-11 for a liquid membrane-forming compound for curing concrete, type 1, class B, meeting the maximum 72-hour water loss requirement of $\leq 0.55 \text{ kg/m}^2$ (ASTM C 156). According to the test report of the Danish Technological Institute, the indicative water loss rate of ISOCURE-SB is 0.46 kg/m^2 (Certificate No.: 790141).

Fields of application

ISOCURE-SB is used as an anti-evaporation agent for fresh concrete and as a surface hardener for existing brittle floors and surfaces

in order to increase their abrasion resistance and reduce wear.

It is particularly useful on large surfaces of exposed concrete, such as industrial floors, car parks, concrete slabs, etc. Also suitable for vertical surfaces.

Technical data

Consistency:	solvent-based, acrylic resins
Color:	transparent
Density:	$0.9 \pm 0.03 \text{ kg/l}$
Solids content:	~ 22% (by weight)
Adhesive strength:	$\geq 2 \text{ N/mm}^2$ (concrete failure)
Abrasion strength (EN 13892-4, BCA):	$\leq 50 \mu\text{m}$, AR0.5
Foot traffic:	after at least 1 h (at $23 \pm 2^\circ\text{C}$ and $50 \pm 5\% \text{ RH}$)
Recoat time:	25 min at $+20^\circ\text{C}$ (substrate temperature)

Directions for use

1. Substrate preparation

Fresh concrete:

ISOCURE-SB is applied on the surface of the fresh concrete, right after smoothing it out with a power trowel.

Hardened concrete:

The surfaces to be treated must be:

- dry and stable;
- free from materials preventing adhesion, such as dust, loose materials, etc.

Moreover, depending on the nature of the substrate, it should be properly prepared by brushing, grinding, milling, sandblasting, water blasting, shot blasting, etc. Following this, the surface should be well cleaned from dust using a high suction vacuum cleaner.

ISOCURE-SB

2. Mixing

ISOCURE-SB is a ready-to-use product. Mix for about 2-3 minutes using a low speed mixer (300 rpm).

3. Application

ISOCURE-SB can be applied using a spray or a special varnish roller in one layer or two for a better result. The second layer is applied after the first one has dried.

Tools should be cleaned with the special solvent SM-16 while ISOCURE-SB is still fresh. If material is hardened, tools can be mechanically cleaned.

Consumption

100-200 ml/m²/layer, depending on application conditions.

Packaging

Supplied in 20 l and 200 l containers.

Shelf life – Storage

12 months after production date if stored in original, unopened packaging at temperatures ranging from +5°C to +25°C. Protect the product from direct sunlight and frost.

Remarks

- ISOCURE-SB has a high solvent content. When applied in confined spaces, ensure proper ventilation.
- In case of overcoating, old coating layers must be removed by grinding the concrete surface, e.g., using a terrazzo polishing machine.
- The temperature of the substrate must be at least 3°C above the dew point to avoid condensation.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory h, type SB is 750 g/l (2010) for the ready-to-use product. The ready-to-use product ISOCURE-SB contains a maximum of 750 g/l VOC.



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

18

EN 13813 SR-B2.0-AR0.5

Synthetic resin screed material for use internally
in buildings

DoP No.: ISOCURE-SB/1611-01

Reaction to fire: F_{fl}

Release of corrosive substances: SR

Water permeability: NPD

Wear resistance: AR0.5

Adhesion: B2.0

Sound insulation: NPD

Sound absorption: NPD

Thermal resistance: NPD

Chemical resistance: NPD

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

Thessaloniki: 17th km Thessaloniki - Ag. Athanasios

P.O. Box 1043, 570 03 Ag. Athanasios

Tel.: 2310 576 000 Fax: 2310 722 475

Athens: 57th km Athens - Lamia Highway, 320 11 Oinofyta

Tel.: 22620 56 406 Fax: 22620 31 644

www.isomat.eu e-mail: info@isomat.eu

